

A Quality Product from Hawkeye Industries Inc.

Duratec® Polyester Sanding Primer 707-007



A high quality polyester sanding primer that provides outstanding filling and leveling properties for many varied substrates.

Usage

For composites, metal, MDF, brick, concrete, various low-density foams, plaster and clay.

Features

Here's why you should choose Duratec Polyester Sanding Primer:

Low porosity—provides a super fine leveling and filling system on a variety of substrates with superior release properties.

Adhesion to most epoxies — with heat distortion level of 201°F, 94°C, the primer also adheres to fiberglass, properly prepared metal,

wood, MDF, brick, concrete and polyurethane foam.

Rapid coat buildup—to 40 mils, 1000 microns, wet on wet, on composite plug and master mold surfaces; saves time and labor cost.

Easy sanding—saves time and effort. An exceptional primer for topcoating with Duratec Surfacing Primers and Hi-Gloss Coatings, lacquers and polyurethane paints.

Duratec Polyester Sanding Primer

707-007 Lt. Grey



Hawkeye Industries Inc.

P O Box 415 Bloomington, CA 92316

Tel 909-546-1160; Toll Free 800-977-0060; Fax: 909-546-1161

Email hawkeyesales@hawkeyeind.com Web www.duratec1.com

Liability/warranty statement: Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.

Duratec is a registered trademark of Dura Technologies Inc.



Product No. 707-007 Lt. Grey

Data Sheet
Continued

Pg. 2

Duratec Polyester Sanding Primer

Product Properties

All time calculations are based on temperatures of 77°F, 25°C

Viscosity

*As measured on a Brookfield Viscometer
Model RVF, Spindle #5 at 2.5 rpm*

2300-2600 cps

Thixotropic Index

5

Gel Time

*Sample based on a 100 g mass,
catalyzed at 2 percent with mekP*

18-22 min

Weight per Gallon

10.90 lb., 4.95 kg

Coverage per Gallon

10 mil thickness

110-115 ft²

250 micron thickness

10.2-10.7 m²

Duratec Polyester Sanding Primer is among the many fine Duratec products marketed worldwide by Hawkeye Industries Inc.

Revised 11-19-15



Hawkeye Industries Inc.

P O Box 415 Bloomington, CA 92316

Tel 909-546-1160; Toll Free 800-977-0060; Fax: 909-546-1161

Email hawkeyesales@hawkeyeind.com Web www.duratec1.com

Liability/warranty statement: Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.

Duratec is a registered trademark of Dura Technologies Inc.