



**P-76 FIBERBOND
REPAIR FILLER
GLASS REINFORCED
POLYESTER FILLER PASTE**

PRODUCT BULLETIN



www.axson-technologies.com
31200 Stephenson Hwy

800.344.7776
Madison Heights, MI 48071

axsonmh@axson.com
Ph 248.588.2270 Fax 248.588.5909

DESCRIPTION

P-76 FiberBond Repair Filler is the ultimate choice for tackling large cracks and abrasions on your boat's deck, hull, keel transom, etc. This fiberglass reinforced filler is specially formulated for heavy duty jobs requiring increased impact strength and durability and is compatible with fiberglass, wood, metals, and most plastics. P-76 FiberBond Repair Filler is water resistant allowing for above or below the waterline applications. The finish can be sanded, machined, tapped, or painted.

TYPICAL HANDLING CHARACTERISTICS @ 77°F (25°C)

Mix Ratio w/BPO Cream Hardener (parts by weight)	100R/2H
Color.....	Dark Green
Consistency.....	Creamy Non-Sag Paste
Application Temperature (minimum temp. recommended).....	55°F (13°C)
Specific Gravity	1.38 g/cc
Work Life	4-6 minutes
Cure to Handling Strength.....	15-20 minutes
Peak Exotherm Temperature	197°F (92°C)
Shelf Life (in original unopened containers)	1 year
Storage Requirement	40°F - 80°F (4°C-27°C)

TYPICAL PHYSICAL PROPERTIES

Ultimate Tensile Strength (ASTM D-638.94B).....	2,419psi (17MPa)
Tensile Elongation (ASTM D-638.94B)	1.3%
Tensile Modulus (ASTM D-638.94B).....	398,300psi (2,746MPa)
Ultimate Flexural Strength (ASTM D-790.92)	4,360psi (30MPa)
Flexural Modulus (ASTM D-790.92)	216,100psi (1,490MPa)
Ultimate Compressive Strength (ASTM D-695.91).....	3,505psi (24MPa)
Compressive Modulus (ASTM D-695.91).....	63,000psi (434MPa)
Heat Deflection Temperature @ 66 psi (ASTM D-648.82)	130°F (55°C)
Heat Deflection Temperature @ 264 psi (ASTM D-648.82)	120°F (49°C)
Average Moisture Absorption (ASTM D-570.81)	1.15%
Coefficient of Linear Thermal Expansion (TMA) (PPM°F (°C)).....	29 (52)
Hardness (ASTM D-2240.91).....	83 Shore D
Adhesive Pull Off Strength (ASTM D-2240.91)	
Substrate: Epoxy - Glass Laminate	420psi (3MPa)
Mahogany.....	850psi (6MPa)

P-76 FiberBond Tech/Revised 1/26/15
Supersedes FiberBond 6/17/14

The information contained in this technical data sheet results from research and tests conducted in our laboratories under precise conditions. Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. It is the responsibility of the user to determine the suitability of the Axson Technologies' products, under their own conditions, before commencing with the proposed application. In no event shall Axson Technologies, Inc. be liable for any direct, indirect, punitive, incidental, special, and/or consequential damages, to property or life, whatsoever arising out of or connected with the use or misuse of our products.

AXSON TECHNOLOGIES US +1 248 588 2270 axsonmh@axson.com axson-na.com	CHINA +86 21 58 68 30 37 marketing.china@axson.com	GERMANY +49 6 07 44 07 11-0 verkauf@axson.com	INDIA +91 20 25 56 07 10-11 info.india@axson.com	ITALY +39 02 96 70 23 36 axson@axson.it	JAPAN +81 5 64 26 25 91 sales.japan@axson.com	FRANCE Global Headquarters +33 1 34 40 34 60 axson@axson.com axson-technologies.com
	MEXICO +52 55 52 64 49 22 marketing@axson.com.mx	MIDDLE EAST +971 7 2432227 axsonmiddleeast@axson.com	SLOVAKIA +42 1 76 42 25 26 axson.sk@axson.com	SPAIN +34 9 32 25 16 20 spain@axson.com	U.K. +44 16 38 66 00 62 sales.uk@axson.com	